# **ANTI FIRE WOOD VARNISH**



stant, water-based, intumescent and transparent thin-film coating used for the protection of the wooden surfaces in the interior against fire. The ANTI FIRE WOOD VARNISH applied surfaces must be protected by ISONEM LIQUID GLASS liquid glass application from water and humidity. Thanks to its transparent structure, when applied, it provides a surface with a highly fire-retardant performance without changing the color of the surface. If a different color is desired, a coloring agent may be applied to the surface before the application. It is environmentally friendly. It does not contain VOC and solvent, it is extremely simple to apply.

#### FEATURES / ADVANTAGES

- Water-based, environmentally friendly.
   Prevents spreading of the flame on the wooden surface.
- With its superior fire-retardant performance, prevents the wood from being ignited immediately.
- Slows down the speed of fire progress.
- Does not emit toxic fumes.
- Provides additional safety against fire in closed and risky places where people are gathered.
- Easy to using. It can be applied with a spray/brush/roll.

#### USAGE AREAS

- Raw wood surfaces, wooden doors
- · Interior furniture,
- Historical monuments, finished wooden buildings,
   Hotels, theaters, entertainment venues, computer rooms, and other public facilities

#### APPLICATION INFORMATION

Surface preparation: Application surfaces should be cleaned from all kinds of oil, dirt, dust and surface wastes and must be completely dry and clean. Primer application is recommended on highly absorbent and exposed surfaces such

as raw wood. For primer application, **ISONEM LIQUID GLASS** product is used with a consumption of 75 - 100 g/m<sup>2</sup>. **Preparation of mixture: ISONEM ANTI FIRE WOOD VARNISH** is supplied in ready-to-use kits according to the mixing ratio. Prepare an amount of mixture to be applied by considering the mixture life. Before starting to mix, make sure that temperatures of the materials are between +15 and +25°C. Stir component A with a 300 – 400 rpm mechanical mixer for 3-4 minutes without dragging air in it. Then, pour the entire component B into component A and make sure that no material is left in component B. Stir component A and B at least for 3 min. until a homogenous mixture is obtained and consume the prepared mixture within 40-45 minutes.

Application Method: ISONEM ANTI FIRE WOOD VARNISH should be applied by brush, roller or spray to obtain the desired thickness, it should be applied as 2 or 3 coats, wait for 18 - 24 hours for each coat, ISONEM ANTIFIRE WOOD VARNISH is not water and moisture resistant. Therefore, after the product fully dry, the following day should be applied as a solvent-based ISONEM LIQUID GLASS protective topcoat in 2 coats and waiting for a minimum of 4 hours between coats.

TECHNICAL SPECIFICATIONS
• Density A+B comp. (25°C, g/mL)
• Viscosity A+B comp. (25°C, mPa.s)

 $1.27 \pm 0.10$ 1500 - 2500 30 minutes Water

· Pot life (23°C) · Solvent ·Color · Product consumption

Transparent 0,3 - 0,5 kg/m<sup>2</sup> (2 layers) · Paintable (Coverage) Area : 3 - 5 m<sup>2</sup>/set

### PACKAGING & STORAGE

1,5 kg set (Component A: 1 kg, Component B: 0.5 kg) · Packaging

e temperature (°C)

· Storage condition Store tightly closed in a dry and cool place.



The surface should be protected from rain, water, mechanical loads and impacts for 72 hours during and after the application.

## APPLICATION CONDITIONS and RISKS The application surface must be clean and free from all impurities like dirt, oil, and mud. onsider during After the product fully dry, the following day should be applied as a solvent-based ISONEM LIQUID GLASS protective topcoat. Other ISONEM ecommended









**General Features** 





Transparent Does not disturb the

Application

temperature

	CONCRETE	MARBLE, GRANITE	RAWWOOD	TILE, CERAMICS	MEMBRANE, SHINGLE	STEEL, METAL
Application	Х	X	In the same direction as the first layer	X	Х	Х
Surface Humidity	Х	X	Dry surface	Х	X	Х
Application Tools	Х	X	Roller, brush, spray	X	X	Х
Primer Usage	Х	X	X	X	Х	Х
Primer Consumption	Х	X	X	Х	Х	Х
Product Usage	Х	X	2 Layers	Х	Х	X
Product Consumption	Х	X	0,300 - 0,500 kg/m² (2 Layers)	Х	Х	Х
Between Two Coats	Х	Х	18 - 24 Hours	Х	Х	х
Touch-free Drying	Х	X	18 - 24 Hours	Х	Х	X
Through Drying	Х	Х	7 Days	X	Х	Х

Note: Drying times are approximate data, it may vary depending on ambient conditions.











