

Report

TestName	WVTR test	Machine	TSY-W1	
Batch	01-01	Mark	GB	
Sample	PET/AL/PE	TestDate	25.04.2011	
TestArea	3,80cm ²	Amount	4	
Company	Labthink	Thick-1	125um	
Standard	ASTM E398	Thick-2	125um	
Operator	MERKEN	Thick-3	125um	
From	Labthink	Thick-4	125um	
Provider	Labthink			
Chamber	WVTR(g/m ² .24hr)	Coefficient	Temp.	RH%
1	189.12	4.125E-03	38 C	80%RH
2			0 C	80%RH
3	137.07	2.974E-03	38.1 C	80%RH
4			0 C	80%RH

Graph

